

Durastat[®] LD-100

Durastat[®] Anti-static Masterbatch for LDPE and LLDPE

Durastat[®] LD-100 is a static dissipative concentrate which can be letdown in LDPE at a concentration of 4-6% in cast or blown film processes and extruded and co extruded bubble processes to meet the electrical performance requirements of United States Military Specification B 81705-C. Durastat[®] LD-100 will provide similar performance in LLDPE and LDPE / LLDPE Blends.

Typical LD-100 Properties in LDPE Film

Property	Units	Typical Value	Test Method
Specific Gravity	g/cm ³	1.02	ASTM-D-792
Electrostatic Decay	sec.	0.6	MIL 81057C
Surface Resistivity	Ohms/sq	<1012	ASTM D-257

*3% Durastat LD-100 in 2mil LDPE film aged 48 hrs. at 12% relative humidity

Polycarbonate stress crack performance: (2 mil film with 3 % Durastat[®] LD-100)

<u>73°F</u> >3400 psi	<u>120°F</u> >3400 psi	<u>158°F</u> 1700 psi	<u>185°F</u> 1700 psi
--------------------------	---------------------------	--------------------------	--------------------------

Durastat[®] Masterbatches Improve YOUR Final Product Quality

Adequate mixing is essential to developing maximum performance from anti-static additives. Since the anti-static ingredients in Durastat[®] Masterbatches are thoroughly wetted with plastic, they are much more easily dispersed than individual dry ingredients. As a result, the use of concentrates rather than dry powders can improve both the anti-static and physical properties of the end product, and in many cases permit a lower loading.

Cleaner, More Efficient Production with Durastat Masterbatches

Plastics processors who use concentrates rather than dry powders benefit from a clean plant with minimal housekeeping. Employee dust exposure likewise is minimized. And there are fewer materials to inventory.

Materials handling is simplified with free-flowing, non-bridging concentrates that can be transferred easily with pneumatic conveyors.

Further, concentrates increase product efficiency through higher production rates with less power consumption and higher yields because additive loss is reduced. There's also less abrasion and equipment wear with concentrates.

Handling and Use

Durastat anti-static compounds and concentrates are considered to be non-hazardous under normal conditions.

Material Safety Data Sheets are available on all these products, and you are encouraged to read and understand these documents before using the product. Since these products are used at elevated temperatures, fumes may be generated under some use conditions. Ventilation is necessary to minimize employee exposure to these fumes.

Packaging and Samples

Standard packaging for concentrates is in 1,000-lb boxes, lined and on pallets. Optional are 250-lb fiber drums and 50-lb bags. To meet particular needs, boxes up to 1,400 lb can be supplied.

Samples are available on request by calling Polymer Products' toll-free order number: 1-800-836-8589.

*Important: The descriptions, designs, and data contained herein are presented for your information only. Because there are many factors under your control which may affect processing or applications/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, and data furnished by Polymer Products hereunder are given gratis and Polymer Products assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk. Any laboratory flammability tests set forth herein are not intended to reflect hazards prescribed by materials under actual fire conditions. As governmental regulations and use conditions may change, it is the Buyer's responsibility to determine the suitability of Polymer Products' products for specific applications.